



MIAMI Masonry Cement Types N, S, M

Manufacturer:

Fairborn Cement Company
 3250 Linebaugh Rd
 Xenia, OH 45385
 800-762-0040 / www.fairborncement.com

Product Description:

Fairborn Cement Company's MIAMI masonry cements are specifically formulated and manufactured to produce masonry mortar for use with concrete masonry units, brick, stone, decorative stone and cultured stone masonry construction applications.

MIAMI masonry cement is a high quality, versatile product formulated with finely ground Portland cement, mineral additives, specialty admixtures and pigments to meet a wide variety of construction requirements including colored masonry cement. All constituent materials are proportioned at the cement plant under strict quality conditions to consistently provide users with a quality product.

Types:

MIAMI masonry cements conform to the physical requirements of ASTM C91. MIAMI masonry cements are manufactured in Type N, Type S and Type M strengths for use in preparing ASTM C270 Type N, S or M mortar. MIAMI masonry cements are designed to be mixed with clean water (free of injurious amounts of any substances that may be harmful to mortar or metal accessories in the masonry) and sand conforming to ASTM C144. No further additions are required or recommended.

For a general guide of mortar type to be used based on construction application, refer to ASTM C270. Other factors to consider are type and absorption of masonry units, exposure and climatic conditions, applicable building codes and engineering requirements.

Quality:

Fairborn Cement Company is committed to quality and takes pride in the products we manufacturer. We manufacture products using only high quality raw materials and strict quality

control procedures. Fairborn Cement Company is the local leader in quality cement production.

Standards:

The following standards apply to the use of Fairborn Cement Company's Masonry Cements:

ASTM C91 (Standard Specification for Masonry Cements).

ASTM C270 (Standard Specification for Mortar).

ASTM C780 (Standard Practice for Pre-Construction and Construction Evaluation of Mortar for Plain and Reinforced Unit Masonry).

ASTM C144 (Standard Specification for Aggregates for Masonry Mortar).

Preparation:

Preparation of masonry mortar using MIAMI masonry cement is to be prepared in accordance with ASTM C270 under either the Proportion Specification or Property Specification Requirements as dictated by the project specifications.

Table 1: Proportion Specification (Proportions by Volume)

Mortar Type	Masonry Cement Type N	Masonry Cement Type S	Masonry Cement Type M	Mason Sand
N	1	-	-	2 ¼ - 3
S	-	1	-	2 ¼ - 3
M	-	-	1	2 ¼ - 3

Table 2: Property Specification

Mortar Type	Compressive Strength min., psi	Water Retention min., %	Air Content max., %
N	750	75	20
S	1800	75	18
M	2500	75	18

The property specification proportions for cement to sand ratios are to be in the range of 1:2 ¼ to 1:3 ½. Compressive strength, water retention and maximum air content should meet the requirements of Table 2.

Fairborn Cement Company

MIAMI Masonry Cement Types N, S, M

Under the property specification, no changes shall be made to the accepted laboratory established proportions in the field, other than water content.

If materials other than those used to establish conformance are to be used in the work, reestablishing conformance to the property specification is required.

Mixing of the mortar should be accomplished by means of a mechanical paddle mixer whenever possible. While the mixer is running, 1) Add 2/3 of the potable water. 2) Add ½ of the ASTM C144 sand. 3) Add MIAMI masonry cement. 4) Add the remaining ASTM C144 sand. 5) Add the remaining potable water to achieve the desired consistency and mix for a minimum of 5 minutes.

Hot Weather:

Hot sun, drying winds and summer temperatures can lead to rapid evaporation of the mixing water from the prepared mortar. This evaporation of water can lead to reduced workability and shorten the life of the mortar. Precautions such as shading materials and mixer, covering transfer equipment and dampening mortar boards should be used to combat the effects of hot weather.

Cold Weather:

Prepared mortar should be mixed and maintained at a temperature above 40°F as prescribed by cold weather masonry specifications. Common methods used to meet this requirement are by heating the mixing water or aggregate. Protection of the newly installed mortar should also follow the prescribed methods outlined in cold weather masonry specifications.

Product Precautions:

Products may cause severe burns and injuries to the skin, eyes, lungs and digestive system. Avoid contact with skin and eyes. Wash exposed skin with soap and water. In case of eye contact, flush eyes immediately and thoroughly, and in both instances consult a physician immediately. Breathing product dust may cause nose, throat or lung irritation or choking. Prolonged exposure to products may cause lung injury, including silicosis and products may contain crystalline silica, a substance that may cause lung cancer. If breathing becomes difficult due to exposure, remove exposed person to fresh air and consult a physician. Gross ingestion of products may cause digestive system injuries or intestinal discomfort. If ingestion occurs do

NOT induce vomiting, but drink plenty of water and consult a physician. Keep out of the reach of children. Follow directions and warnings on Product packaging.

For other precautions please refer to the Fairborn Cement Company's Masonry Cement SDS Report.

Availability:

Type N, S, and M MIAMI masonry cement is available in bulk or bagged quantities at:

3250 Linebaugh Road
Xenia, OH 45385

Also available through a vast network of partnering distribution companies.

Additional Information:

Additional information can be provided by visiting:
www.fairborncement.com

Warranty:

LIMITED WARRANTY. The products shall conform to applicable specifications of the American Society for Testing and Materials, and such other specifications.

Seller, having no control over the use of the product does not guarantee finished work, nor shall seller be responsible for the condition of the Product after delivery to the buyer. Charges incident to inspection or testing made by or on behalf of buyer to determine compliance with specifications shall be paid for by buyer.

EXCEPT FOR THE LIMITED WARRANTY MADE ABOVE, SELLER SPECIFICALLY DISCLAIMS ANY OTHER WARRANTY, INCLUDING ANY EXPRESS WARRANTY, ANY IMPLIED WARRANTY OF MERCHANTABILITY OF GOODS, AND ANY IMPLIED WARRANTY OF FITNESS OF GOODS FOR ANY PARTICULAR PURPOSE, ALL OF SUCH WARRANTIES ARE EXCLUDED AND SPECIFICALLY DISCLAIMED BY SELLER.