



3250 Linebaugh Rd.
 Xenia, OH 45385
 Telephone (800) 762-0040
 FAX (937) 879-8425

**CEMENT
MILL
TEST**

Cement Identified as: **Masonry Cement, Type S** **Date:** **06/28/21**
Production Dates: **May, 2021**

PHYSICAL REQUIREMENTS	SPECIFICATIONS	ASTM C 91 Type S	RESULTS
(ASTM C 430) 45-um sieve, % retained	Maximum	24	10
(ASTM C 151) Autoclave Expansion, %	Maximum	1.0	0.11
(ASTM C 266) Time of Setting (Gillmore)			
Initial Set, minutes	Minimum	90	245
Final Set, minutes	Maximum	1000	383
(ASTM C 185) Air Content, %	Range	8-19	18
(ASTM C 1506) Water Retention	Minimum	70	82
(ASTM C 109) Compressive Strength, psi (Mpa)			
7 Day	Minimum	1300 (9.0)	1825 (12.6)
28 Day	Minimum	2100 (14.5)	2180 (15.0)

'We hereby certify that this cement conforms to all of the standard requirements for masonry cement in the above specification for the type specified.

By: *Rusty Strader*

Physical Testing completed by: DG, MS
 Chemical Testing completed by: TA, NC, KL, NM

Rusty Strader
 Quality Control Manager
 Fairborn Cement Company