



3250 Linebaugh Rd.  
 Xenia, OH 45385  
 Telephone (800) 762-0040  
 FAX (937) 879-8425



**Cement Identified as:** Mortar Cement, Type S **Date:** 06/28/21  
**Production Dates:** May, 2021

PHYSICAL REQUIREMENTS	ASTM C 1329 SPECIFICATIONS Type S			RESULTS
(ASTM C 430) 45-um sieve, % retained	Maximum	24		9
(ASTM C 151) Autoclave Expansion, %	Maximum	1.0		0.18
(ASTM C 266) Time of Setting (Gillmore)				
Initial Set, minutes	Minimum	90		240
Final Set, minutes	Maximum	1000		300
(ASTM C 185) Air Content, %	Range	8-19		13
(ASTM C 1506) Water Retention	Minimum	70		78
(ASTM C1072) Flexural Bond Strength (psi)	Minimum	100		102
(ASTM C 109) Compressive Strength, psi (Mpa)				
7 Day	Minimum	1300 ( 3.5 )		3020 ( 20.8 )
28 Day	Minimum	2100 ( 14.5 )		3640 ( 25.1 )

We hereby certify that this cement conforms to all of the standard requirements for mortar cement in the above specification for the type specified. ASTM C1072 testing is performed by an independent testing firm and results are available upon request.

By: Rusty Strader

Physical Testing completed by: DG, MS  
 Chemical Testing completed by: TA, NC, KL, NM

Rusty Strader  
 Quality Control Manager  
 Fairborn Cement Company