



3250 Linebaugh Rd.
 Xenia, OH 45385
 Telephone (800) 762-0040
 FAX (937) 879-8425

**CEMENT
MILL
TEST**

Cement Identified as: Mortar Cement, Type N **Date:** 12/30/19
Production Dates: November, 2019

PHYSICAL REQUIREMENTS	ASTM C 1329 SPECIFICATIONS			RESULTS
		Type N		
(ASTM C 430) 45-um sieve, % retained	Maximum	24		7
(ASTM C 151) Autoclave Expansion, %	Maximum	1.0		0.1
(ASTM C 266) Time of Setting (Gillmore)				
Initial Set, minutes	Minimum	120		215
Final Set, minutes	Maximum	1000		320
(ASTM C 185) Air Content, %	Range	8-21		13
(ASTM C 1506) Water Retention	Minimum	70		76
(ASTM C 109) Compressive Strength, psi (Mpa)				
7 Day	Minimum	500 (3.5)		2640 (18.2)
28 Day	Minimum	900 (6.2)		3020 (20.8)

We hereby certify that this cement conforms to all of the standard requirements for mortar cement in the above specification for the type specified. ASTM C 1357 testing is performed by an independent testing firm and results are available upon request.

By: *Rusty Strader*

Physical Testing completed by: DG, MS
 Chemical Testing completed by: TA, NC, JD, NM

Rusty Strader
 Quality Control Manager
 Fairborn Cement Company