



3250 Linebaugh Rd.
 Xenia, OH 45385
 Telephone (800) 762-0040
 FAX (937) 879-8425

**CEMENT
MILL
TEST**

Cement Identified as: Mortar Cement, Type N **Date:** 12/01/21
Production Dates: October, 2021

PHYSICAL REQUIREMENTS	ASTM C 1329 SPECIFICATIONS			RESULTS
		Type N		
(ASTM C 430) 45-um sieve, % retained	Maximum	24		6
(ASTM C 151) Autoclave Expansion, %	Maximum	1.0		0.12
(ASTM C 266) Time of Setting (Gillmore)	Minimum	120		165
	Maximum	1000		295
(ASTM C 185) Air Content, %	Range	8-21		14
(ASTM C 1506) Water Retention	Minimum	70		80
(ASTM C1072) Flexural Bond Strength (psi)	Minimum	70		85
(ASTM C 109) Compressive Strength, psi (Mpa)	Minimum	500 (3.5)		2630 (18.1)
	Minimum	900 (6.2)		3140 (21.7)

We hereby certify that this cement conforms to all of the standard requirements for mortar cement in the above specification for the type specified. ASTM C1072 testing is performed by an independent testing firm and results are available upon request.

By: *Rusty Strader*

Physical Testing completed by: DG, JT
 Chemical Testing completed by: TA, NC, KL, NM

Rusty Strader
 Quality Control Manager
 Fairborn Cement Company